



奧迪美®

BP138

BASE PLASTER (WATERPROOF)

GENERAL PURPOSE WATERPROOF WALL RENDER

PRODUCT DESCRIPTION

OPTIMIX BP138 BASE PLASTER (WATERPROOF) is a high quality polymer modified cementitious wall render modified with waterproofing additives to reduce the movement of water.

Specially formulated for ease of installation and quick finishing, **OPTIMIX BP138 BASE PLASTER (WATERPROOF)** is ideal for spray or hand application.

Capable of high build application up to 25mm thick in one layer, **OPTIMIX BP138 BASE PLASTER (WATERPROOF)** bonds strongly to the substrate and hardens to a strong, durable water resistant finish ideal for internal or external walls.



TYPICAL USAGE

- Waterproofing render onto interior or exterior concrete, brick or block walls
- Spray application for rapid levelling of large scale projects
- Simple hand application for small and large scale projects
- Refurbishment and New Build Projects

FEATURES AND BENEFITS

- Excellent Water Resistance
- Good Strength & Bond Performance
- Consistent, Simple and Easy to Use
- Improve Surface Finish
- Complies with the relevant parts of ASD General Specification cl18.61 (2022) including BS8481 & EN13914
- Complies with EN998-1
- Environmentally Friendly

TECHNICAL DATA

Product Characteristics	OPTIMIX BP138
Compressive Strength at 28 days	~ 15 MPa
Flexural Strength at 28 days	~ 4.5 MPa
Bond to Concrete at 28 days	~ 1.0 MPa
Water Absorption (ISAT) @10, 30, 60min	< 0.1 ml/m ² ·s
Water Retentivity	99%
Water Impermeability Pressure	0.7 MPa
Thickness (Nominal Build-up)	10 - 25 mm in 1 coat
	25 - 40 mm in 2 coats
Pot Life at 27°C	Approx. 1 hour
Wet Density	1,800 kg/m ³
Water Demand	6.5 - 7.5 liters
Coverage	1.5 kg/mm/m ²
Packaging (per bag)	40 kg
Shelf Life	12 months

Note: The above are typical laboratory test results and can vary slightly depending on the ambient and substrate conditions during application.

Testing Methods	
Flow and Density	BS 4551
Compressive and Flexural Strength	BS EN 1015-11
Pull-off Test	HKHA/MTS (2000), Part D 2.1.15
Water Absorption (ISAT)	BS 1881: Part 208
Water Retentivity	BS 4551 : Part 1 : 1998
Water Impermeability Pressure	JC/T 894 – 2001 (App. A)
VOC Content	USEPA Method 24

Note: The tests were performed according to the national standard or in-house modifications of the corresponding testing procedures.

Environmental Data	
Volatile Organic Compounds (VOC)	≤ 10 g/L
Potential BEAM points	Product is manufactured within 800km of Hong Kong project sites
Packaging Composition	Paper bags incorporating 40% recycled paper



Complied Standards	
Complies with the relevant parts of ASD General Specification cl18.61 (2022 & legacy) including:	
BS EN 8481 : 2006	Design, preparation and application of internal gypsum, cement, cement and lime plastering systems – Specification.
BS EN 13914-1 : 2016	Design, preparation and application of external rendering and internal plastering. External rendering.
BS EN 13914-2 : 2016	Design, preparation and application of external rendering and internal plastering. Internal plastering.
BS EN 998-1 : 2016	Specification for mortar for masonry. Rendering and plastering mortar.



INSTALLATION GUIDE

(Refer to Method Statement for more details)

SURFACE PREPARATION

OPTIMIX BP138 can be applied direct to a suitably sound and prepared substrate that is free from shrinkage, settlement or other significant movement.

Substrate must be clean, free from loose particles, oil, grease and other contaminants.

It is recommended to pre-wet the substrate with potable water overnight or before application if the weather or surface is under a very dry condition.

OPTIMIX PROCRETE Spatterdash mix may be used to improve the wet and tensile adhesion especially on smooth or dense substrates such as off-formed concrete.

OPTIMIX PROCRETE Spatterdash can be applied within 48 hours of striking formwork, and after the surface is cleaned and allowed to become surface dry. Applied spatterdash should be allowed to harden for a minimum of 2 days and preferably 7 days or more before applying the render.

MIXING

Hand Mixing:

Mix one bag of **OPTIMIX BP138** dry powder with 6.5 – 7.5 L potable water by using an electrical forced action mixer. For easy mixing add the required amount of water to the mixer, begin mixing and add the powder and continue to mix for about 3 minutes or until a lump-free homogeneous mix is achieved.

Spray Mixing:

Mix and spray the mortar simultaneously with the use of special continuous mixing and pumping equipment. Follow the pump manufacturers' instructions closely. When continuously spraying adjust the water gauge to achieve the correct workability at the nozzle.

Correctly applied material will initially appear slightly glossy, it may sag briefly and slightly during spraying, but it will exhibit virtually no rebound.

APPLICATION

Application thickness should be between approximately 10mm and up to around 25mm per layer. For application in excess of 25mm multiple layers are required; Initial layers should be left rough-finished as a key. Additional layers should be applied once the first layer has achieved sufficient strength to support the application, finishing and curing of subsequent layers.

FINISHING AND CURING

Depending on application method and site conditions, **OPTIMIX BP138** will remain highly workable and easy to finish for around 15 to 30 minutes; High temperatures and strong drying influences will reduce the working time. For best results, the final layer of **OPTIMIX BP138** should be struck off level as soon as possible after application, while the material is at its most workable. This is especially important when spraying as surfaces will tend to dry out more quickly. Finishing the surface as soon as possible will make the job easy for the worker, ensure the best bond performance and result in the best surface finish. Finishing can be achieved using a wooden float to give a keyed surface or a steel trowel to achieve a smooth surface. For a smooth surface wait until the surface firms up then carefully strike off using one or two passes of a trowel cleaned with a damp cloth.

Additional curing is not normally required but in instances of hot or strong drying then a traditional curing compound can be applied once the surface has hardened.



LIMITATIONS

Whilst no special curing treatments are normally required Optimix recommend protecting the installation from significant drying influences at least overnight and preferably longer if the site situation allows.

HEALTH AND SAFETY

OPTIMIX BP138 is alkaline in nature and can cause irritations to persons with sensitive skin. Avoid inhalation of dust and contact with skin and eyes. Wear suitable protective gloves and masks while handling the product. If contact with eyes, rinse immediately with plenty of clean water and seek medical advice. This product is non-toxic and is not flammable.

STORAGE

Store the products in a cool and dry place with the original unopened bags on pallets with plastic wrapping. Protect from direct sunlight, rainfall and exposure to high humidity conditions. Avoid excessive stacking of pallets. Failure to comply with the recommended storage conditions may result in premature deterioration of the product or packaging and reduce shelf life.

ALTERNATIVE PRODUCTS

Other similar products in the Optimix range include:

- **BP126** Base Plaster
- **BP168** Base Plaster (Premium)



Important Note: The information contained herein is, the best of our knowledge, true and reliable and is supported by the present state of our knowledge. No warranty is given or implied in connection with any recommendations or suggestions made by us or our representatives as the conditions of use and any labour involved are beyond our control.



OPTIMIX (HONG KONG) LIMITED
 20/F, SUP Tower, 75-83 King's Road, North Point, Hong Kong

☎ (852)2395 5388 🛒 (852)2802 6433
 🏥 (852)2802 6408 🌐 www.optimix.com.hk

